



Hood Distribution

NASHVILLE BRANCH

126 International Blvd., La Vergne, TN 37086
Phone: 1-615-793-7746 • Fax: 1-615-793-3700
www.hooddistribution.com
"FSC" Certified

DOMESTIC PLYWOOD

www.columbiaforestproducts.com

Alder Birch Natural
Birch White Cherry
Cypress Hickory
Knotty Pine Mahogany
Maple Natural Maple White
Walnut Afr. Mahogany
Red Oak Ash
White Oak Shop Grade
Rustic Grades Beaded Plywood

Poplar - Poplar/Aspen - FIR - MDF - CROSSBAND CORES
** 4X8-4X10 ** CARB 2 / NAF / TSCA TITLE VI
"Purebond" NAF

ACCOYA

www.accoya.com
4/4 - 10/4

REMANUFACTURING HARDWOODS

S2S - S4S - Straight Line Rip, Gang Rip and
mouldings, T&G

MELAMINE - ROSEBURG/KRONOSPAN

www.rfpco.com
White Black Hardrock Drawer sides
*Other colors in stock

DOMESTIC LUMBER

Alder Basswood Walnut
Birch Cherry Cypress
Hickory Maple Hard Maple Soft
Red Oak White Oak Poplar
Ash

IMPORT LUMBER

Red Grandis Jatoba
African Mah
Mahogany
Sapele

SOFTWOOD LUMBER

Furniture Grade Pine SYP
Aromatic Cedar Western Red Cedar

EDGE BANDING

www.formwood.com
Hickory Maple White Birch
White Oak Red Oak White/Black
Walnut Cherry Mahogany
Prefinished - Pre glued - Peel & Stick

IMPORT PLYWOOD

Birch White Meranti/Lauan NZ Pine
Liner Russian Birch Maple
Drawer sides Light weight

RADIATA PINE PLYWOOD

www.aruacoply.com

MARINE PLYWOOD

www.weyerhaeuser.com
AB Fir / Starboard / MDO
Marinetech

KNAPE & VOGT

www.kv.com
Sliding Systems - Barn Door Hardware - Standards &
Brackets - Kitchen & Bath

EVERLAST ADVANCED COMPOSITE SIDING

www.everlastsiding.com

HETTICH

Drawer Slides

CHOICE BRAND ADHESIVES

www.choicebrandadhesives.com

FORMICA LAMINATES

www.formica.com

STARBOARD

www.kingplastic.com
ST Panels & Custom Doors
Colorcore Plastaball Color Board

COMPOSITE PANELS

Kerfkore Ultra-light MDF
Particleboard EXTIRA MDF
Medex MDF MDF Domestic
ARRIES MDF Medite Fire Rated MDF
Beaded MDF

* All panel products CARB2/TSCA Title VI

BENDING PLYWOOD

Meranti - Barrel Column //KERFCORE//

HARDWOOD VENEERS

www.formwood.com
Paper Back - Poly Back - Wood Back - Peel & Stick
Reconstituted Hardwood Veneers
Architectural Laid Up Hardwood Plywood Panels

MISCELLANEOUS

www.titebond.com
Tite Bond Glue
Deerwood fasteners
Reclaimed lumber
Decorative panels

LET HOOD HELP YOU WITH YOUR SPECIALTY NEEDS

On-Time, On Grade, Competitively Priced
#Hoodwoodisgood

EST. 1899

HOOD DISTRIBUTION - NHLA LUMBER GRADES

This chart summarizes the main requirements for the standard grades. For complete information, consult the appropriate section of the NHLA Rule Book.

	FAS	FIF	SELECT	#1 COM	#2 & 2B	#3A COM	#3B COM	FAS LIMITS	
Minimum Size Board	6" x 8"	Same as FAS for species being graded	4" x 6"	3" x 4"	3" x 4"	3" x 4"	3" x 4"	<p>PITTH= SM in inches Wane= 1/2 Length Knot= 1/3 SM Warp= Entire board must be flat enough to S2S to S.S.T. Splits: not to exceed 2 x SM or 12" whichever is greater. Splits shall not diverge 1" in 12" First Lineal Foot Rule: Applies to both ends of Board, to contain not over 25% unsound wood.</p>	<p>Wane in FASIFACE: FAS transmission applies to better face. #1 Common Side: 1/3W or 1/2L. Widest wane added together: Length can be on both edges.</p>
Minimum Size Cutting	4" x 5' 3" x 7'			4" x 2' 3" x 3'	3" x 2'	3" x 2'	Not less than 1 1/2" wide containing 36 sq. inches		
Basic Yield	SM x 10 83-1/3%	<p>BETTER FACE TO GRADE FAS POOR FACE TO GRADE #1 COMMON</p>		SM x 8 66-2/3%	SM x 6 50%	SM x 4 33-1/3%	SM x 3 25%	<p>Wane in Selects: Pcs. 6" & Wider FAS limitation applies to Better face. #1 Common side: 1/3W or 1/2L. Widest wane added together. Length can be on both side. Pcs. 4" & 5" Wide 1/3W or 1/2L applies to both faces. Add widest wane together. Add total length of wane from both edges.</p>	
Formula to Determine Number of Cuts	SM _____ 4 (4 max.)		SM+1 _____ 3 (5 max.)	SM _____ 2 (7 max.)	Unlimited	Unlimited	Unlimited		Unlimited
SM Needed to Take Extra Cutting	6-15' SM			3-10' SM	2-7' SM				
Extra Yield Needed for Extra Cutting	SM x 11 91-2/3%			SM x 9 75%	SM x 8 66-2/3%				
Special Yields	97% Rule - 2 cuts full width any length. Pcs. 6" & wider with 6-12" SM SM x 11.64 for Yield	97% Rule On Better Face	2 + 3 SM to be 100% clear or SM x 11 in one cutting on Better Face. 97% Rule	1' SM- 100% 2' SM SMx 9	1' SM SMx 8 2A Com- Clear Face Cuttings 2B Com- Sound Cuttings	2A Com on Better Face and reverse side of cuttings sound; will also qualify for 3A Com			

#hoodwoodisgood
On-Time, On Grade, Competitively Priced
 Est 1899